



SAF™ PA12 - Powered by Evonik Datasheet

SAF™ PA12 - Powered by Evonik is a cost-efficient production material developed to help manufacturers scale additive manufacturing while maintaining the performance expected from PA12. Processed with Stratasys SAF™ technology on the H350™ 3D printer, it delivers strong, resilient, and dimensionally accurate parts with the consistency required for industrial applications.

Introduced in partnership with Evonik, a global leader in high-performance polymers, this material combines proven PA12 mechanical performance with improved production economics. Faster print speeds and optimized material pricing enable a lower total cost per part while maintaining reliable build-to-build quality.

With seamless integration into the SAF workflow, SAF™ PA12 Powered by Evonik is designed to support efficient, scalable production across a wide range of end-use applications.

Property	Mean	Unit	Standard*
Tensile Strength (XZ,YX)	47 (6,817)	MPa (psi)	ASTM D638-14
Tensile Strength (ZX)	45 (6,672)	MPa (psi)	ASTM D638-14
Elongation at Break (XZ,YX)	11	%	ASTM D638-14
Elongation at Break (ZX)	5	%	ASTM D638-14
0.2% Offset Yield Strength (XZ,YX)	33.5 (4,859)	MPa (psi)	ASTM D638-14
0.2% Offset Yield Strength (ZX)	32.2 (4,670)	MPa (psi)	ASTM D638-14
Tensile Modulus (XZ,YX)	1,750 (254)	MPa (ksi)	ASTM D638-14
Tensile Modulus (ZX)	1,700 (247)	MPa (ksi)	ASTM D638-14
Flexural Strength (XZ,YX)	40 (5,801)	MPa (psi)	ASTM D790-17
Flexural Strength (ZX)	41 (5,946)	MPa (psi)	ASTM D790-17
Flexural Modulus (XZ,YX)	900 (131)	MPa (ksi)	ASTM D790-17
Flexural Modulus (ZX)	925 (134)	MPa (ksi)	ASTM D790-17
Notched Impact Strength (XZ,YX)	4.17 (1.98)	kJ/m ² (Ft.lbf/in ²)	ASTM D256-10
Notched Impact Strength (ZX)	3.36 (1.60)	kJ/m ² (Ft.lbf/in ²)	ASTM D256-10

* Testing based on stated ASTM standards with the following exceptions: tests performed at ambient laboratory conditions (approximately 21 °C and ambient humidity). Samples not conditioned as per stated methods prior to testing.



General	Mean	Unit	Standard
Part Specific Gravity	0.98		ASTM D792-13
Virgin Particle Size D50	56 (2.2)	µm (thou)	
Virgin Powder Melting Point	185 (365)	°C (°F)	

Disclaimer:

¹ Customer acknowledges the contents of this document and that Stratasys parts, materials, and supplier are subject to its standard terms and conditions, available on <http://www.stratasys.com/legal/terms-and-conditions-of-sale>, which are incorporated herein by reference.

² The specifications and/or information on which this document is based are subject to change without notice.

³ The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Tested parts were built on the Stratasys H350 3D printer. Product specifications are subject to change without notice. The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the Stratasys material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.



stratasys.com

ISO 9001:2015

Certified

Stratasys Headquarters
5995 Opus Parkway,
Minnetonka, MN 55343
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

1 Holtzman St.
Science Park
Rehovot, 7670401
Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

MATERIAL DATA SHEET
SAF

© 2026 Stratasys. All rights reserved. Stratasys, the Stratasys Signet logo, Stratasys Direct Manufacturing, H350, H Series, SAF, Selective Absorption Fusion, Big Wave and HAF are trademarks or registered trademarks of Stratasys Inc. and/or its affiliates. The H350 printer is subject to a license from Loughborough University Enterprises Limited and Evonik IP GmbH under the following and/or related patents and patent applications and their family members: EP2739457, EP3539752, EP1648686, EP 1740367, EP1737646, EP1459871. Further details including live and in-force status of family members may be found at <https://worldwide.espacenet.com/patent/search/family/>. All other trademarks are the property of their respective owners, and Stratasys assumes no responsibility with regard to the selection, performance, or use of these non Stratasys products. Product specifications subject to change without notice. MDS_SAF_PA12 Powered by Evonik_0326a