

PT8958

URETHANE CASTING MATERIAL SPECIFICATIONS

Highlights

- MR Transparent the material will not image at 1.5 T in proton signal testing, with one test site showing no proton of magnetic susceptibility at both 1.5 and 3.0 T
- UL 94 V-0 Certified (flammability testing) per IEC 60695 11-10

TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES ENGLISH **TEST METHOD** METRIC Clear Light Amber Clear Light Amber **Color/Appearance** Visual **Compressive Modulus** ASTM D695 401,980 psi 2,771 MPa ASTM D695 87 MPa 12,690 psi **Compressive Strength** Density ASTM D792 0.0430 lb/in3 1.19 g/cc ASTM D638 34% 34% **Elongation at Break Flexural Modulus** ASTM D790 422,913 psi 2,915 MPa ASTM D790 116 MPa 16.935 psi **Flexural Strength** Heat Deflection Temperature @ 66 psi ASTM D648 175°F 79°C 97°C Glass Transition Temperature Tg (peak) ASTM D4065 207°F Izod Impact Strength (method A, notched) ASTM D256 1.70 ft-lb/in 90 J/m Shore D Hardness ASTM D2240 85 D 85 D **Tensile Modulus** ASTM D638 389,590 psi 2,686 MPa **Tensile Strength** ASTM D638 11,380 psi 78 MPa

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.



INFO@STRATASYSDIRECT.COM / STRATASYSDIRECT.COM

©2017 Stratasys Direct, Inc. All rights reserved. Stratasys, Stratasys signet and Stratasys Direct Manufacturing are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. Last update 05/2017

Applications

- Non hand-held equipment for the MRI coil industry
- Products requiring a UL 94 V-0 flammability rating